

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : D04H 3/16, 3/14, D01D 5/08	A1	(11) International Publication Number: WO 00/15891 (43) International Publication Date: 23 March 2000 (23.03.00)
(21) International Application Number: PCT/US99/21348 (22) International Filing Date: 14 September 1999 (14.09.99) (30) Priority Data: 60/100,192 14 September 1998 (14.09.98) US (71) Applicant: CEREX ADVANCED FABRICS, L.P. [US/US]; 610 Chemstrand Road, Pensacola, FL 32533 (US). (72) Inventors: ORTEGA, Albert, E.; 3489 River Gardens Circle, Pensacola, FL 32514 (US). THOMLEY, R., Wayne; 8138 Lawton Road, Pensacola, FL 32514 (US). MACKEY, Jan; 1046 Edgewater Lane, Gulf Breeze, FL 32561 (US). (74) Agents: SALIWANCHIK, David, R. et al.; Saliwanchik, Lloyd & Saliwanchik, Suite A-1, 2421 NW 41st Street, Gainesville, FL 32606-6669 (US).		(81) Designated States: JP, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: NONWOVEN FABRICS (57) Abstract This invention relates to nonwoven fabrics with advantageous characteristics and the method to produce these fabrics. Advantageously, the fabrics of the subject invention have increased thickness (loft) compared to conventional nonwoven fabrics and have high air permeability and open space while maintaining softness and strength at the same basis weight.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

DESCRIPTION

NONWOVEN FABRICS

5

Field of the Invention

10 This invention relates to new nonwoven fabrics having advantageous properties. The fabrics have unique filament characteristics which impart improved properties to the fabrics.

Background of the Invention

15 Nonwoven fabrics and numerous uses thereof are well known to those skilled in the textiles art. Such fabrics can be prepared by forming a web of continuous filament and/or staple fibers and bonding the fibers at points of fiber-to-fiber contact to provide a fabric of requisite strength. The term "bonded nonwoven fabric" is used herein to denote nonwoven fabrics wherein a major portion of the fiber-to-fiber bonding is adhesive bonding accomplished via incorporation of adhesives in the web to "glue" fibers together or autogenous bonding such as
20 obtained by heating the web or by the use of liquid or gaseous bonding agents (usually in conjunction with heating) to render the fibers cohesive. In effecting such bonding, particularly autogenous bonding, the web may be subjected to mechanical compression to facilitate obtaining adequate bonding. Mechanical compression normally sets the loft or thickness of fabrics with similar basis weights. It is well known that thickness is increased by increasing the basis weight,
25 or the mass per square area.

 Spunbonded nonwoven fabrics formed of nylon, polyester, polypropylene, or other man-made polymers are widely used commercially for a number of purposes. Such fabrics exhibit excellent strength and permeability properties and accordingly are desirable for use in construction fabrics, filtration material, and furniture and bedding backing materials.

30 The fabrics are produced via the well-known spunbonding process in which molten polymer is extruded into filaments, and the filaments are attenuated and drawn pneumatically and deposited onto a collection surface to form a web. The filaments are bonded together to produce a strong, coherent fabric. Filament bonding is typically accomplished either thermally or chemically, *i.e.*, autogenously. Thermal bonding is accomplished by compression of the web

of filaments between the nip of a pair of cooperating heated calender rolls thereby setting the thickness. In autogenous bonding of nylon filaments, the web of filaments is transported to a chemical bonding station or "gashouse" which exposes the filaments to an activating agent (*i.e.*, HCl) and water vapor. Water vapor enhances the penetration of the HCl into the filaments and causes them to become tacky and thus amenable to bonding. Upon leaving the bonding station, the web passes between rolls which compress and bond the web thereby setting the thickness. Adequate bonding is necessary to minimize fabric fuzzing (*i.e.*, the presence of unbonded filaments) and to impart good strength properties to the fabric. Autogenous bonding has been used extensively in forming spunbonded nylon industrial fabrics.

Nonwoven fabrics which are strongly bonded overall (for example, by uniform compression of the entire web in the presence of heat and/or appropriate bonding agents) tend to be stiff and boardy and are frequently more similar to paper than to woven textile fabrics. In order to obtain softer nonwoven fabrics more closely simulating woven fabrics, nonwoven "point-bonded" fabrics have been prepared by processes which tend to limit bonding to spaced, discrete areas or points. This is accomplished by application or activation of an adhesive or bonding agent and/or application of heat and/or pressure at the points where bonding is desired. For example, the web to be bonded can be compressed between a pair of rolls or platens, at least one of which carries bosses or a land and groove, design sized and spaced to compress the web at the desired points. The compression device can be heated to effect thermal bonding of the web fibers or to activate a bonding agent applied to the web.

In the actual practice of preparing point-bonded fabrics, however, it is frequently difficult or even impossible to limit bonding to the desired points. In many processes, web areas between the desired bond points are subjected to sufficient heat, compression, activated bonding agent, or adhesive to effect "tack" bonding of fibers outside the desired bond points. Such tack bonding is believed to contribute significantly to undesired fabric stiffness.

It has been found that most point-bonded nonwoven fabrics, particularly those having a large number of tack bonds, and many overall bonded nonwoven fabrics can be significantly softened by subjecting the fabric to mechanical stress. For example, the fabric can be washed in conventional domestic washing machines, drawn under tension over a sharply angled surface such as a knife blade, stretched, twisted, crumpled, or subjected to various combinations of such treatments. Such treatments are believed to effect softening primarily by breaking weaker fiber-to-fiber bonds such as tack bonds which can be broken without breaking the point- or intentionally-bonded fibers. These methods are relatively effective but subject to certain practical problems. For example, drawing a nonwoven fabric over a knife blade with sufficient

force to effect substantial softening frequently results in an undesirably high level of physical damage to the fabric. Washing of nonwoven fabrics generally yields good results, but is a batch operation not typically adaptable for use in continuous processes of the type employed commercially for production of nonwoven fabrics.

5 Another method for softening nonwoven fabrics is by impinging the fabric with a fluid jet. This is, however, an additional and potentially cumbersome production step, resulting in increased manufacturing costs.

It is apparent that a commercially practical process for a simpler, more cost-effective method for the softening of nonwoven fabrics while maintaining other advantageous physical properties such as strength and thickness would satisfy a long-felt need in the nonwoven textile art.

10 Thickness (loft) of nonwoven fabrics is normally determined by the basis weight. Increasing the basis weight adds cost due to the use of more raw materials. It is desirable to have increased thickness (loft) in some applications where these fabrics are used without increasing the basis weight.

15 Openness (air permeability) of nonwoven fabrics is also normally determined by the basis weight and method of bonding. In some applications, it is desirable to have a fabric with increased openness (air permeability) in some applications without increasing the basis weight.

20 Nonwoven fabrics are also used in a variety of coating applications. Coating materials will be captured and held more effectively onto a fabric that is more open. Fabrics that use less coating to effect the same desired results would be more cost effective. Fabrics with greater fiber surface area can also increase the effectiveness of the coating process.

Brief Summary of the Invention

25 The subject invention concerns a novel improved process for producing nonwoven fabrics with improved characteristics. The subject invention further pertains to the fabric produced by the process described herein. In an embodiment specifically exemplified herein, the nonwoven fabric of the subject invention is made of nylon.

30 Specifically, the subject invention provides a process for providing fabrics which have desired characteristics in terms of thickness, permeability, tensile strength, and hand (softness). In a preferred embodiment, the production of a nonwoven nylon fabric is improved by modifying the denier per filament (dpf). An important advantage of the process of the subject invention is that it provides a fabric with enhanced thickness, open space, and permeability while maintaining excellent strength and desirable softness characteristics of the nonwoven fabric.

In specific embodiments, the fabrics of the subject invention can have round filaments, crescent filaments, multilobal filaments, diamond filaments and/or hollow filaments. The multilobal filaments have at least two lobes and, preferably, three or more lobes. In a preferred embodiment the filaments are trilobal. The use of multilobal filaments is particularly advantageous for maximizing coatings since these filaments have more surface area.

The fabrics of the subject invention may have a dpf ranging from about 0.5 dpf to about 20 dpf. In another preferred embodiment, round filaments will be from about 4 to about 12 dpf and multilobal filaments will be from about 5 to about 12 dpf.

Detailed Disclosure of the Invention

In the following detailed description of the subject invention and its preferred embodiments, specific terms are used in describing the invention; however, these are used in a descriptive sense only and not for the purpose of limitation. It will be apparent to the skilled artisan having the benefit of the instant disclosure that the invention is susceptible to numerous variations and modifications within its spirit and scope.

The present invention concerns a process to produce spunbonded nonwoven fabrics with advantageous properties. The subject invention further concerns the fabrics produced according to the subject processes.

Advantageously, the fabrics of the subject invention have increased thickness (loft) compared to conventional nonwoven fabrics and have high air permeability and open space while maintaining softness and strength at the same basis weight. The weight of the fabric of the subject invention will typically be between about 0.2 ounces per square yard and about 7 ounces per square yard. In a preferred embodiment, the weight of the fabric produced as described herein is about 0.5 ounce per square yard. The advantageous characteristics of the fabrics of the subject invention are achieved utilizing filaments having round, crescent, diamond, hollow, and/or multilobal cross-sections.

In one embodiment, the fabrics of the present invention comprise at least two different denier sizes of filaments wherein the larger denier filaments comprise at least about 5% of the filaments. Preferably, the larger denier filaments comprise at least about 25% of the filaments. More preferably, the larger denier filaments comprise at least about 28.5% of the filaments.

In a preferred embodiment the fabrics of the subject invention can contain round and/or trilobal cross sections. The denier per filament (dpf) can be modified as described herein to give desired characteristics. Table 1 lists characteristics of specific fibers which can be used according to the subject invention.

Table 1. Cross Section and Expected DPF of Novel Nonwoven Fabrics							
Item	Bottom side of Fabric Cross Section	Bottom Side DPF	Top Side of Fabric Cross section	Top Side DPF	Thickness (mils)	Air Permeability	Basis Weight (osy)
1	ROUND	4	ROUND	4	6.48	1039	0.490
2	ROUND	4	ROUND	12	7.26	1241	0.506
3	ROUND	4	TRILOBAL	5	6.48	1028	0.546
4	ROUND	4	TRILOBAL	12	7.19	1233	0.484
5	ROUND	12	ROUND	4	9.13	1213	0.472
6	ROUND	12	ROUND	12	7.47	1280	0.474
7	ROUND	12	TRILOBAL	5	9.66	1185	0.537
8	ROUND	12	TRILOBAL	12	8.39	1376	0.470
9	TRILOBAL	5	ROUND	4	6.41	1049	0.530
10	TRILOBAL	5	ROUND	12	7.36	1204	0.527
11	TRILOBAL	5	TRILOBAL	5	6.70	1069	0.521
12	TRILOBAL	5	TRILOBAL	12	6.82	1195	0.470
13	TRILOBAL	12	ROUND	4	8.08	1165	0.511
14	TRILOBAL	12	ROUND	12	8.05	1454	0.483
15	TRILOBAL	12	TRILOBAL	5	8.88	1121	0.506
16	TRILOBAL	12	TRILOBAL	12	8.34	1332	0.468

Fabrics with high denier per filament counts and multilobal filaments provide fabrics with increased thickness and the most open space. The fabrics of the present invention can be at least about ten deniers. Preferably, a fabric of the present invention is about twelve denier. In one example, a fabric with twelve denier, trilobal filaments is permeable and can be used alone in filtration applications or as a coarse layer in a composite filter. This fabric can also be used for needle punch applications. The increased thickness and open space of these fabrics can also hold coating material which is desirable in applications that use wax, adhesive, latex or other coatings.

The subject invention further concerns fabrics with mixed filament cross sections. These fabrics can be produced by, for example, installing spinnerets with capillaries of different

cross sections on different positions, sides or beams of the machine. Spinnerets with different capillary cross sections or capillary sizes within the same spinneret can also be used.

5 The fabrics of the subject invention have more opacity, stronger tensile properties and hold more coating material than fabrics made with only round cross section filaments. For example, the trilobal filaments add strength by the way they pack on the fabric and add opacity by the way they reflect light. They also hold more coating material since trilobal filaments have more surface area. Similarly, a multilobal cross section also imparts these same or better desirable properties.

10 Fabrics made with twelve denier filament cross sections have more open areas than fabrics made with lower denier cross sections, thus yielding higher air permeability and better coating properties. Fabrics with twelve denier, trilobal cross section filaments have even better coating characteristics since they are more open and have higher surface area.

15 The fabrics of the subject invention can be produced by extruding a plurality of continuous filaments, directing the filaments through an attenuation device to draw the filaments, depositing the filaments onto a collection surface such that a web is formed, and bonding the filaments together either autogenously or thermally to form a coherent, strong fabric. For example, the filaments can be autogenously bonded to one another at discrete points throughout the fabric. Preferably, about 5% to about 50% of the filaments are bonded to one another at discrete points throughout the fabric. More preferably, about 18% to about 22% of
20 the filaments are bonded to one another at discrete points throughout the fabric.

Typically, the filaments of the invention are composed of nylon or other man-made fibers from polymers such as polyester, polyolefins, polypropylene, polyethylene or other polyamides or combinations of such can be used. Also, mixtures of polymers can be used. Preferably, the nylon compound will be nylon 6, 6 and/or nylon 6. In one embodiment, polyethylene, polypropylene, and/or polyester can be added to the nylon material. This produces
25 a softer feel and increases water repellency. In the case of polyethylene, the polyethylene should have a melt index between about 5 grams/10 min and about 200 grains/10 min and a density between about 0.85 grains/cc and about 1.1 grams/cc. The polyethylene can be added at a concentration of about 0.05% to about 20%.

30 The filaments produced during the process of the subject invention may be bonded, for example, chemically, ultrasonically, or thermally. In one embodiment, HCl gas and water vapor can be applied to achieve bonding. In another embodiment, the filaments are heated to, for example, between 180°C and about 250°C. Preferably, the filaments are heated to between about 200°C and 235°C.

In one embodiment, a nonwoven fabric of the subject invention is made of a plurality of polymeric filaments bonded to one another to form a nonwoven web with a basis weight between about 0.2 ounces per square yard and about 7.0 ounces per square yard, and preferably comprises at least two different denier sizes of filaments such that the larger denier filaments
5 comprise at least about 5% of the filaments. Preferably, the larger denier filaments of the fabric are at least about 1.5 times larger than the smaller denier filaments. More preferably, the larger denier filaments of the fabric are at least about twelve denier. In a preferred embodiment, a fabric of the invention comprises at least about 25% of larger multilobal or round filaments while the remaining filaments comprise smaller multilobal or round filaments. Preferably, the
10 larger filaments are about twelve denier and the smaller multilobal filaments are five denier and the smaller round filaments are four denier.

In one embodiment, the nonwoven fabric of the invention comprises at least about 25% larger round and multilobal filaments, with at least about 5% large, multilobal filaments, the balance of the large filaments being of round cross section with the balance being smaller denier
15 multilobal or round filaments or a combination of both. In a further embodiment, the nonwoven fabric of the invention comprises at least about 25% larger round and multilobal filaments, with at least about 5% large, round filaments, the balance of the large filaments being of multilobal cross section and the balance being smaller denier multilobal or round filaments. In a preferred embodiment, the larger filaments are either twelve denier multilobal or round filaments or both,
20 and the smaller filaments are five denier multilobal or four denier round filaments or both.

The subject invention also concerns methods of producing a thicker more open nonwoven fabric. In one embodiment, the method comprises providing at least two different denier sizes of filaments such that the larger denier filaments are at least about 5% of the filaments and directing a plurality of these filaments onto a collection surface to form a web and
25 forming a multiplicity of discrete bond sites in the fabric to bond together the large and small filaments. In one embodiment, the larger filaments of the fabric are produced by reducing the number of capillaries in at least about 5% of the spinnerets and maintaining a constant mass flow of polymer. In another embodiment, the larger filaments can be produced by changing the diameter or cross section of some of the capillaries within the spinnerets, or by reducing the
30 amount of drawforce on undrawn larger filaments. Where the larger filaments are produced by reducing the amount of drawforce, the drawforce can be reduced, for example, by aspiration of undrawn filaments or by decreasing the distance between the spinneret and an attenuation device.

In the methods of the subject invention, the formation of discrete bond sites in the fabric to bond together the larger and small filaments can be accomplished by heating the web of filaments in discrete areas and forming thermal bonds. In a preferred embodiment, the discrete thermal bonds comprise from about 5% to about 50% of the fabric area. More preferably, the discrete thermal bonds comprise from about 16% to about 24% of the fabric area.

All patents, patent applications, provisional applications, and publications referred to or cited herein are incorporated by reference in their entirety to the extent that are not inconsistent with the explicit teachings of this specification.

Following are examples which illustrate procedures for practicing the invention. These examples should not be construed as limiting. All percentages are by weight and all solvent mixture proportions are by volume unless otherwise noted.

Example 1

Seven fabric samples were made using nylon 6,6 polymer by installing eighty hole spinnerets with a round cross section on one side of the block fed by an extruder and thirty-two hole spinnerets with either a round or trilobal cross section on the other side. Twenty-eight and a half percent of the filaments of these seven fabric samples were twelve denier filaments. The nylon 6,6 polymer was melted and extruded at a temperature of about 295°C. Filaments were attenuated and drawn pneumatically using aspirating jets and deposited onto a laydown or forming box. The resulting webs were then directed to a calender where about 20% of the surface area was bonded at discrete points at a temperature of about 216°C. The thickness, air permeability and basis weights of these seven fabric samples are shown in Table 2. The average thickness, air permeability and basis weight of these fabrics are 7.74 mils, 1213 cubic feet per minute per square foot (cfm/ft²) and 0.496 ounces per square yard (osy), respectively. The deniers per filament (DPF's), the maximum distance between filaments (MDBF) and the area of the holes in the fabric (HOLE AREA) were measured on two samples, items 34 and 44. Item 34 has DPF's of 11.4 for the round filaments and 3.7 for the trilobal filaments, an MDBF of 1185 microns and a HOLE AREA of 435,093 square microns. Item 44 has DPF's of 11.8 for the round filaments and 4.1 for the trilobal filaments, an MDBF of 761 microns and a HOLE AREA of 205,323 square microns.

Table 2. Properties of fabrics made with eighty and thirty-two hole spinnerets						
Item	Bottom Side of Fabric Cross Section	Bottom Side Spinneret Capillaries	Top Side Spinneret Capillaries	Thickness (mils)	Air Permeability (cfm/ft ²)	Basis Weight (osy)
34	ROUND	32	ROUND	80	9.14	0.472
44	TRILOBAL	32	ROUND	80	8.78	0.514
64	TRILOBAL	32	ROUND	80	7.38	0.507
52	ROUND	80	ROUND	32	7.33	0.497
53	ROUND	80	TRILOBAL	32	7.53	0.514
72	ROUND	80	ROUND	32	7.20	0.515
73	ROUND	80	TRILOBAL	32	6.85	0.454

For comparison, six fabrics were made using the same process substituting eighty hole spinnerets with a round cross section on both sides of the machine. This fabric is currently available commercially under the trade name of "PBN-II" as Type 30 by CEREX Advanced Fabrics, L.P. The results of these fabrics are shown in Table 3. The average thickness, air permeability and basis weight of these fabrics are 6.48 mils, 1039 cfm/ft² and 0.490 osy, respectively. The DPF, MDBF and HOLE AREA were measured on one sample from this fabric set, item 82. Item 82 has a DPF of 5.0, an MDBF of 585 microns and a HOLE AREA of 108,400 square microns. Three more fabrics were made using the same process substituting eighty hole spinnerets with a round cross section on one side of the machine and a sixty-four hole spinneret with a trilobal cross section on the other side of the machine. The results of these fabrics are shown in Table 4. The average thickness, air permeability and basis weight of these fabrics are 6.45 mils, 1035 cfm/ft² and 0.540 osy, respectively. A third set of five fabrics was made similarly using the same process substituting sixty-four hole spinnerets with a trilobal cross section on both sides of the machine. This fabric is currently available commercially under the trade name of "PBN-II" as Type 31 by CEREX Advanced Fabrics, L.P. The results of these fabrics are shown in Table 5. The average thickness, air permeability and basis weight of these fabrics are 6.70 mils, 1069 cfm/ft² and 0.521 osy, respectively. The DPF's, MDBF and HOLE AREA were measured on one sample from this fabric set, item 13. Item 13 has a DPF of 5.0, an MDBF of 403 microns and a HOLE AREA of 78,450 square microns.

Table 3. Properties of fabrics made with eighty hole spinnerets

Item	Bottom Side of Fabric Cross Section	Bottom Side Spinneret Capillaries	Top Side Spinneret of Fabric Cross Section	Top Side Spinneret Capillaries	Thickness (mils)	Air Permeability (cfm/ft ²)	Basis Weight (osy)
54	ROUND	80	ROUND	80	7.10	1029	0.506
74	ROUND	80	ROUND	80	6.48	981	0.463
81	ROUND	80	ROUND	80	6.88	1014	0.529
82	ROUND	80	ROUND	80	5.83	1078	0.470
83	ROUND	80	ROUND	80	6.48	1050	0.491
84	ROUND	80	ROUND	80	6.15	1084	0.484

Table 4. Properties of fabrics made with eighty and sixty-four hole spinnerets

Item	Bottom Side of Fabric Cross Section	Bottom Side Spinneret Capillaries	Top Side Spinneret of Fabric Cross Section	Top Side Spinneret Capillaries	Thickness (mils)	Air Permeability (cfm/ft ²)	Basis Weight (osy)
24	TRILOBAL	64	ROUND	80	6.41	1049	0.530
51	TRILOBAL	80	TRILOBAL	64	6.45	1045	0.567
71	ROUND	80	TRILOBAL	64	6.50	1011	0.524

Table 5. Properties of fabrics made with sixty four hole spinnerets

Item	Bottom Side of Fabric Cross Section	Bottom Side Spinneret Capillaries	Top Side Spinneret of Fabric Cross Section	Top Side Spinneret Capillaries	Thickness (mils)	Air Permeability (cfm/ft ²)	Basis Weight (osy)
11	TRILOBAL	64	TRILOBAL	64	6.25	1114	0.536
12	TRILOBAL	64	TRILOBAL	64	6.88	1109	0.508
13	TRILOBAL	64	TRILOBAL	64	6.08	1117	0.511
14	TRILOBAL	64	TRILOBAL	64	7.10	1034	0.497
21	TRILOBAL	64	TRILOBAL	64	7.20	970	0.554

The average thickness of the seven fabrics listed in Table 2 was higher than all three fabric sets listed in Tables 3, 4, and 5. The thickness of a fabric made with eighty-hole spinnerets with a round cross section on one side of the block fed by an extruder and thirty-two hole spinnerets with either a round or trilobal cross section on the other side was 1.04 mills higher than the average of the Type 31 fabrics; 1.29 mills higher than the average thickness of the fabrics made with eighty hole spinnerets with a round cross section on one side of the machine and a sixty-four hole spinneret with a trilobal cross section on the other side of the machine and 1.26 mills higher than the average thickness of the Type 30 fabrics.

The average air permeability of the seven fabrics listed in Table 2 was higher than all three fabric sets listed in Tables 3, 4, and 5. The air permeability of a fabric made with eighty-hole spinnerets with a round cross section on one side of the block fed by an extruder and thirty-two hole spinnerets with either a round or trilobal cross section on the other side was 144 cfm/ft² higher than the average of the Type 31 fabrics; 178 cfm/ft² higher than the average air permeability of the fabrics made with eighty hole spinnerets with a round cross section on one side of the machine and a sixty-four hole spinneret with a trilobal cross section on the other side of the machine and 174 cfm/ft² higher than the average air permeability of the Type 30 fabrics. Fabrics made containing twenty-eight and a half percent twelve denier filaments had higher loft (thickness) and higher openness (air permeability) than fabrics made with four denier, round cross section filaments, fabrics made with five denier, trilobal cross section filaments or fabrics made with a mixture of four denier, round cross section and five denier, trilobal cross section filaments.

Example 2

Five fabric samples were made using nylon 6,6 polymer by installing sixty-four hole spinnerets with a trilobal cross section on one side of the block fed by an extruder and thirty-two hole spinnerets with either a round or trilobal cross section on the other side. Thirty-three percent of the filaments of these five fabric samples were twelve denier filaments. The nylon 6,6 polymer was melted and formed into webs as described in Example 1. The thickness, air permeability and basis weights of these seven fabric samples are shown in Table 6. The average thickness, air permeability and basis weight of these fabrics are 8.32 mills, 1165 cfm/ft² and 0.509 osy, respectively. The DPF's, MDBF and HOLE AREA were measured on three samples from this fabric set, items 31, 41 and 23. Item 31 has DPF's of 5.3 for the trilobal filaments and 12.2 for the round filaments, an MDBF of 1037 microns and a HOLE AREA of 352,701 square microns. Item 41 has DPF's of 10.6 and 5.6, an MDBF of 437 microns and a HOLE AREA of

81,975 square microns. Item 23 has DPF's of 13.3 and 5.5, an MDBF of 730 microns and a HOLE AREA of 170,721 square microns.

The average thickness of the five fabrics listed in Table 6 was higher than all four fabric sets listed in Tables 2, 3, 4, and 5. The average thickness of fabric made with sixty-four hole spinnerets with a trilobal cross section on one side of the block fed by an extruder and thirty-two hole spinnerets with either a round or trilobal cross section on the other side was 1.62 mills higher than the average of the Type 31 fabrics; 1.87 mills higher than the average thickness of the fabrics made with eighty hole spinnerets with a round cross section on one side of the machine and a sixty-four hole spinneret with a trilobal cross section on the other side of the machine; 1.84 mills higher than the average thickness of the Type 30 fabrics and 0.58 mills higher than the average thickness of fabric made with eighty-hole spinnerets with a round cross section on one side of the block fed by an extruder and thirty-two hole spinnerets with either a round or trilobal cross section on the other side.

The average air permeability of the five fabrics listed in Table 6 was higher than all three fabric sets listed in Tables 3, 4, and 5. The air permeability of a fabric made with sixty-four hole spinnerets with a trilobal cross section on one side of the block fed by an extruder and thirty-two hole spinnerets with either a round or trilobal cross section on the other side was 96 cfm/ft² higher than the average of the Type 31 fabrics; 130 cfm/ft² higher than the average air permeability of the fabrics made with eighty hole spinnerets with a round cross section on one side of the machine and a sixty-four hole spinneret with a trilobal cross section on the other side of the machine and 127 cfm/ft² higher than the average air permeability of the Type 30 fabrics.

Table 6. Properties of fabrics made with sixty-four hole spinnerets and thirty-two hole spinnerets

Item	Bottom Side of Fabric Cross Section	Bottom Side Spinneret Capillaries	Top Side Spinneret of Fabric Cross Section	Top Side Spinneret Capillaries	Thickness (mils)	Air Permeability (cfm/ft ²)	Basis Weight (osy)
31	TRILOBAL	32	TRILOBAL	64	9.66	1185	0.537
41	TRILOBAL	32	TRILOBAL	64	9.03	1157	0.532
61	TRILOBAL	32	TRILOBAL	64	8.73	1084	0.485
22	TRILOBAL	64	ROUND	32	7.36	1204	0.527
23	TRILOBAL	64	TRILOBAL	32	6.82	1195	0.470

Fabrics made containing thirty-three percent twelve denier filaments had higher loft or thickness than fabrics made with four denier, round filaments, fabrics made with twenty-eight and a half percent twelve denier filaments. Fabrics made containing thirty-three percent twelve denier filaments. Fabrics made containing thirty-three percent twelve denier filaments had higher air permeability or openness than fabrics made with four denier, round filaments, fabrics made with five denier, trilobal filaments and fabrics made with a mixture of four denier, round and five denier, trilobal filaments.

Example 3

Six fabric samples were made using nylon 6,6 polymer by installing thirty-two hole spinnerets with either a trilobal or round cross section on one side of the block fed by an extruder and thirty-two hole spinnerets with either a round or trilobal cross section on the other side. All of the filaments of these six fabric samples were twelve denier filaments. The nylon 6,6 polymer was melted and formed into webs as described in Example 1. The thickness, air permeability and basis weights of these seven fabric samples are shown in Table 7. The average thickness, air permeability and basis weight of these fabrics are 8.11 mils, 1371 cfm/ft² and 0.474 osy, respectively. The DPF's, MDBF and HOLE AREA were measured on three samples from this fabric set, items 32, 62 and 63. Item 32 has a DPF of 11.9, an MDBF of 3552 microns and a HOLE AREA of 3,492,177 square microns. Item 62 has DPF's of 12.6 for the trilobal filaments and 11.2 for the round filaments, an MDBF of 2766 microns and a HOLE AREA of 2,719,185 square microns. Item 63 has a DPF of 11.9, an MDBF of 1657 microns and a HOLE AREA of 835,938 square microns.

The average thickness of the five fabrics listed in Table 7 was higher than all four fabric sets listed in Tables 2, 3, 4 and 5. The average thickness of fabric made with thirty-two hole spinnerets with a trilobal or round cross section on one side of the block fed by an extruder and thirty-two hole spinnerets with either a round or trilobal cross section on the other side was 1.41 mills higher than the average of the Type 31 fabrics; 1.65 mills higher than the average thickness of the fabrics made with eighty hole spinnerets with a round cross section on one side of the machine and a sixty-four hole spinneret with a trilobal cross section on the other side of the machine; 1.62 mills higher than the average thickness of the Type 30 fabrics and 0.36 mills higher than the thickness of the average of fabric made with eighty hole spinnerets with a round cross section on one side of the block fed by an extruder and thirty-two hole spinnerets with either a round or trilobal cross section on the other side.

The average air permeability of the five fabrics listed in Table 7 was higher than all five fabric sets listed in Tables 2, 3, 4, 5, and 6. The air permeability of a fabric made with thirty-two hole spinnerets with either a round or trilobal cross section on one side of the block fed by an extruder and thirty-two hole spinnerets with either a round or trilobal cross section on the other side was 302 cfm/ft² higher than the average air permeability of the fabrics made with eighty hole spinnerets with a round cross section on one side of the machine and a sixty-four hole spinneret with a trilobal cross section on the other side of the machine; 332 cfm/ft² higher than the average air permeability of the Type 30 fabrics; 158 cfm/ft² higher than fabrics made with eighty hole spinnerets with a round cross section on one side of the block fed by an extruder and thirty-two hole spinnerets with either a round or trilobal cross section on the other side and 206 cfm/ft² higher than fabrics made with sixty-four hole spinnerets with a trilobal cross section on one side of the block fed by an extruder and thirty-two hole spinnerets with either a round or trilobal cross section on the other side cfm.

Table 7. Properties of fabrics made with thirty-two hole spinnerets							
Item	Bottom Side of Fabric Cross Section	Bottom Side Spinneret Capillaries	Top Side Spinneret of Fabric Cross Section	Top Side Spinneret Capillaries	Thickness (mils)	Air Permeability (cfm/ft ²)	Basis Weight (osy)
32	ROUND	32	ROUND	32	7.47	1280	0.474
33	ROUND	32	TRILOBAL	32	8.39	1376	0.470
42	TRILOBAL	32	ROUND	32	7.93	1521	0.479
43	TRILOBAL	32	TRILOBAL	32	8.23	1301	0.468
62	TRILOBAL	32	ROUND	32	8.18	1387	0.487
63	TRILOBAL	32	TRILOBAL	32	8.45	1362	0.469

10

15

20

Fabrics made containing only twelve denier filaments had higher loft or thickness than fabrics made with four denier, round, filaments, fabrics made with five denier, trilobal filaments, fabrics made with a mixture of four denier, round and five denier, trilobal filaments or fabrics made with twenty-eight and a half percent twelve denier filaments with the remaining filaments being either four denier, round filaments or five denier, trilobal filaments. Fabrics made containing only twelve denier filaments had higher air permeability or openness than fabrics made with four denier, round filaments, fabrics made with five denier, trilobal filaments, fabrics made with twenty-eight and one half percent of the filaments being twelve denier filaments with the remaining filaments being either four denier, round filaments or five denier, trilobal filaments and fabrics made with one third of the filaments being twelve denier filaments with the remaining filaments being either four denier, round filaments or five denier, trilobal filaments.

Example 4

25

The fabrics with twelve denier filaments from examples 1, 2, and 3 can be produced by decreasing the air pressure of specific jets or a slot device fed by spinnerets designed to produce higher denier filaments. The air pressure can be decreased sufficiently to reduce the draw force to produce the desired denier per filament in certain sections of the web.

Example 5

30

The fabrics with twelve denier filaments from examples 1, 2 and 3 can be produced by decreasing the distance between the spinneret and the aspirating device, a jet or slot device, fed by spinnerets designed to produce higher denier filaments. The distance can be decreased

sufficiently to reduce the drawforce to produce the desired denier per filaments in certain sections of the web.

- 5 It should be understood that the examples and embodiments described herein are for illustrative purposes only and that various modifications or changes in light thereof will be suggested to persons skilled in the art and are to be included within the spirit and purview of this application and the scope of the appended claims.

Claims

1 1. A nonwoven fabric comprising a plurality of polymeric filaments bonded to one
2 another to form a nonwoven web with a basis weight between about 0.2 ounces per square yard
3 and about 7.0 ounces per square yard, said fabric comprising at least two different denier sizes
4 of filaments such that the larger denier filaments comprise at least about 5% of the filaments.

1 2. The nonwoven fabric according to claim 1, wherein the larger denier filaments are
2 at least about 1.5 times larger than the smaller denier filaments.

1 3. The nonwoven fabric according to claim 2, wherein the larger denier filaments are
2 at least about twelve denier.

1 4. The nonwoven fabric according to claim 2, wherein the fabric comprises at least
2 about 25% larger multilobal filaments and the balance being smaller denier multilobal or round
3 filaments.

1 5. The nonwoven fabric according to claim 4, wherein the larger multilobal filaments
2 are twelve denier multilobal filaments and the balance are smaller, five denier multilobal or four
3 denier round filaments.

1 6. The nonwoven fabric according to claim 2, wherein the fabric comprises at least
2 about 25% larger round filaments and the balance being smaller denier multilobal or round
3 filaments.

1 7. The nonwoven fabric according to claim 6, wherein the larger round filaments are
2 twelve denier round filaments and the balance are smaller, five denier multilobal or four denier
3 round filaments.

1 8. The nonwoven fabric according to claim 1, wherein the fabric comprises at least
2 about 25% larger round and multilobal filaments, with at least about 5% large, multilobal
3 filaments, the balance of the large filaments being of round cross section with the balance being
4 smaller denier multilobal or round filaments or a combination of both.

1 9. The nonwoven fabric according to claim 1, wherein the fabric comprises at least
2 about 25% larger round and multilobal filaments, with at least about 5% large, round filaments,
3 the balance of the large filaments being of multilobal cross section and the balance being smaller
4 denier multilobal or round filaments.

1 10. The nonwoven fabric according to claim 8, wherein the larger filaments are either
2 twelve denier multilobal or twelve denier round filaments or both and the balance are smaller,
3 five denier multilobal or four denier round filaments or both.

1 11. The nonwoven fabric according to claim 1, wherein the filaments of said
2 spunbonded fabric are autogenously bonded to one another at discrete points throughout the
3 fabric.

1 12. The nonwoven fabric according to claim 11, wherein about 5% to about 50% of the
2 fabric area is bonded to one another at discrete points throughout the fabric.

1 13. The nonwoven fabric according to claim 11, wherein about 18% to about 22% of
2 the fabric area is bonded to one another at discrete points throughout the fabric.

1 14. The nonwoven fabric according to claim 1, wherein said filaments are nylon.

1 15. The nonwoven fabric according to claim 1, wherein said filaments are polyester or
2 polyolefins or a mixture of both.

1 16. A method of producing a thicker more open nonwoven fabric, said method
2 comprising providing at least two different denier sizes of filaments such that the larger denier
3 filaments comprise at least about 5% of the filaments and directing a plurality of these filaments
4 onto a collection surface to form a web and forming a multiplicity of discrete bond sites in the
5 fabric to bond together said large and small filaments.

1 17. The method according to claim 16, wherein the larger filaments are produced by
2 reducing the number of capillaries in at least about 5% of the spinnerets and maintaining a
3 constant mass flow of polymer.

1 18. The method according to claim 16, wherein the larger filaments are produced by
2 changing the diameter or cross section of some of the capillaries within the spinnerets.

1 19. The method according to claim 16, wherein the larger filaments are produced by
2 reducing the amount of drawforce on the undrawn larger filaments.

1 20. The method according to claim 19, wherein the amount of drawforce is reduced to
2 produce larger filaments by reducing the aspiration of the undrawn filaments.

1 21. The method according to claim 19, wherein the amount of drawforce is reduced to
2 produce larger filaments by decreasing the distance between the spinneret and the attenuation
3 device.

1 22. The method according to claim 16, wherein the step of forming discrete bond sites
2 in the fabric comprises heating the web of filaments in discrete areas and forming thermal bonds.

1 23. The method according to claim 22, wherein the discrete thermal bonds comprise
2 about 5% to about 50% of the fabric area.

1 24. The method according to claim 22, wherein the discrete thermal bonds comprise
2 about 16% to about 24% of the fabric area.

1 25. The nonwoven fabric according to claim 9, wherein the larger filaments are either
2 twelve denier multilobal or twelve denier round filaments or both and the balance are smaller,
3 five denier multilobal or four denier round filaments or both.

1 26. The nonwoven fabric according to claim 3, wherein the larger denier filaments are
2 trilobal or round filaments.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 99/21348

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 D04H3/16 D04H3/14 D01D5/08

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 D04H D01D D01F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 660 910 A (HOYT MATTHEW B ET AL) 26 August 1997 (1997-08-26) column 3, line 60 -column 5, line 60; figures 1,2 example 1 ---	1-3, 11, 14-16, 22, 26
X	US 5 752 945 A (OWEN VERA ET AL) 19 May 1998 (1998-05-19) column 1, line 60 -column 3, line 49; claims column 3, line 59 -column 4, line 17 ---	1, 2, 15
X	US 4 107 364 A (SISSON JAMES BRYANT) 15 August 1978 (1978-08-15) example claims 34-39; figures 1-6 ---	1
	--- -/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "A" document member of the same patent family

Date of the actual completion of the international search

15 February 2000

Date of mailing of the international search report

02/03/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3018

Authorized officer

Barathe, R

INTERNATIONAL SEARCH REPORT

International Application No.
PCT/US 99/21348

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	WO 99 23285 A (KIMBERLY CLARK CO) 14 May 1999 (1999-05-14) page 19, paragraph 1 claims page 11, line 11 - line 15 page 9, line 12 - line 18; figure 2 ---	1,15
A	US 5 679 042 A (VARONA EUGENIO GO) 21 October 1997 (1997-10-21) figures 5,8 ---	1-26
A	US 5 431 986 A (ORTEGA ALBERT E ET AL) 11 July 1995 (1995-07-11) the whole document ---	1-26
A	WO 98 30744 A (CEREX ADVANCED FABRICS L P) 16 July 1998 (1998-07-16) the whole document ---	1-26
A	EP 0 421 649 A (AMOCO CORP) 10 April 1991 (1991-04-10) table 5 ---	1
A	EP 0 822 284 A (FREUDENBERG CARL FA) 4 February 1998 (1998-02-04) the whole document -----	1-26

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No
PCT/US 99/21348

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5660910 A	26-08-1997	NONE	
US 5752945 A	19-05-1998	EP 0873737 A	28-10-1998
US 4107364 A	15-08-1978	AU 1463976 A	08-12-1977
		BE 842632 A	06-12-1976
		BR 7603640 A	25-01-1977
		CA 1068889 A	31-12-1979
		CH 600017 A	15-06-1978
		DE 2625236 A	23-12-1976
		DK 250076 A	07-12-1976
		ES 448620 A	01-07-1977
		FR 2401253 A	23-03-1979
		FR 2382535 A	29-09-1978
		GB 1558199 A	19-12-1979
		GB 1558198 A	19-12-1979
		IT 1063345 B	11-02-1985
		JP 52021479 A	18-02-1977
		LU 75089 A	09-03-1977
		NL 7606048 A,B,	08-12-1976
		PH 13410 A	28-03-1980
		SE 7606367 A	07-12-1976
		US 4209563 A	24-06-1980
WO 9923285 A	14-05-1999	US 5965468 A	12-10-1999
		AU 1291299 A	24-05-1999
US 5679042 A	21-10-1997	AU 705458 B	20-05-1999
		AU 2446597 A	12-11-1997
		BR 9708746 A	03-08-1999
		CN 1216589 A	12-05-1999
		EP 0895550 A	10-02-1999
		WO 9740223 A	30-10-1997
US 5431986 A	11-07-1995	AU 3004795 A	16-02-1996
		WO 9602694 A	01-02-1996
WO 9830744 A	16-07-1998	US 5913993 A	22-06-1999
		AU 5732598 A	03-08-1998
		EP 0953076 A	03-11-1999
EP 0421649 A	10-04-1991	US 5173356 A	22-12-1992
		AT 125583 T	15-08-1995
		AU 624268 B	04-06-1992
		AU 6269390 A	11-04-1991
		CA 2025186 A	26-03-1991
		CN 1050749 A,B	17-04-1991
		DE 69021160 D	31-08-1995
		DE 69021160 T	07-12-1995
		DK 421649 T	11-12-1995
		ES 2074540 T	16-09-1995
		JP 3152258 A	28-06-1991
		KR 137651 B	15-05-1998
		NZ 235400 A	26-03-1992
		PT 95394 A,B	22-05-1992
		US 5073436 A	17-12-1991
EP 0822284 A	04-02-1998	DE 19630523 C	12-03-1998

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/US 99/21348

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0822284 A		JP 2813585 B	22-10-1998
		JP 10102370 A	21-04-1998
		PL 321389 A	02-02-1998